

**ELECTRON-PHONON INTERACTION WITHIN THE FRAMEWORK  
OF THE FLUCTUATING VALENCE OF COPPER ATOMS  
- A THEORETICAL MODEL FOR HIGH  
TEMPERATURE SUPERCONDUCTIVITY**

SURESH V. VETTOOR and V. M. NANDAKUMARAN

*Department of Physics, Cochin University of Science and Technology, Cochin-22, India*

Received 24 August 1989

Revised 26 October 1989

Electron-phonon interaction is considered within the framework of the fluctuating valence of Cu atoms. Anderson's lattice Hamiltonian is suitably modified to take this into account. Using Green's function technique the possible quasiparticle excitations are determined. The quantity  $2\Delta_H(0) / k_B T_c$  is calculated for  $T_c = 40$  K. The calculated values are in good agreement with the experimental results.

The recent discovery of superconducting transition at high temperature in ceramic oxides<sup>1,2</sup> necessitates reconsideration of the conventional theoretical framework of superconductivity. The microscopic theory of BCS<sup>3</sup> with phonons plays the role of exchange particle cannot explain superconducting transition at temperatures as high as 40 K or 90 K.<sup>4,5</sup> Experiments show nearly the absence of isotope effect in these ceramic oxides.<sup>6</sup> The  $\text{La}_{2-x}\text{Sr}_x\text{CuO}_4$  and  $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$  group of materials have Cu-O layers which are the conducting planes of the crystal.<sup>7,8</sup> There is strong anisotropy in these materials.<sup>9,10</sup> By substituting Sr atoms with the La atoms of the parent compound  $\text{La}_2\text{CuO}_4$ , we can introduce holes into the oxygen  $2p$  bands of the Cu-O planes.<sup>11</sup> In  $\text{YBa}_2\text{Cu}_3\text{O}_{7-\delta}$  the introduction of oxygen vacancies affects the number of holes in the oxygen  $2p$  bands of the Cu-O planes.<sup>12</sup> It is found that  $T_c$  in these materials have a strong dependence on hole concentration.<sup>13</sup>

Various theoretical models have been suggested to explain superconductivity in these ceramic oxides. Some of these theories assume a model system where the role of the  $2p$  bands is not appropriately taken into account. Hubbard model Hamiltonian with the hopping term and the on site repulsive term are considered to contain the essential interactions to describe the superconducting transition. The RVB theory approaches the situation along these lines.<sup>14</sup> We are of the view that RVB description is correct in the insulating limit where antiferromagnetic

PACS Nos.: 74.20-z, 74.60-w, 74.90 + n.

correlation of the Cu spins is possible. When the material is doped, it leads to the creation of holes in the oxygen  $2p$  bands unfavorably affecting super-exchange interaction between Cu spins. The Copper  $3d^9$  electrons hybridizes with the oxygen  $2p$  bands when there are holes in the  $2p$  bands. The strength of this hybridization depends on the doping concentration. In this framework we are taking into account the interaction of the  $2p$  band electrons with the lattice. Double occupancy of the Cu sites is energy-wise made unfavorable by the Hubbard on site repulsive term.<sup>15</sup> These requirements are satisfied by Andersons lattice Hamiltonian<sup>16</sup> with a few additional terms.

We assume that the electron-electron repulsive interaction is only of the on site Hubbard type and the effective electron phonon interaction can be replaced by a Frohlich type electron-electron interaction term.<sup>17</sup>

Under the above conditions, the Hamiltonian for the system takes the form

$$\begin{aligned}
 H = & \sum_{k,\sigma} \varepsilon_k C_{k,\sigma}^\dagger C_{k,\sigma} + E_0 \sum_{i,\sigma} a_{i,\sigma}^\dagger a_{i,\sigma} + \sum_q \hbar\omega_q b_q^\dagger b_q + U/2 \sum'_{i,\sigma,\sigma'} a_{i,\sigma}^\dagger a_{i,\sigma'} a_{i,\sigma'}^\dagger a_{i,\sigma} \\
 & + V_1 / \sqrt{N} \sum_{i,k,\sigma} \{e^{-ikRi} a_{i,\sigma}^\dagger C_{k,\sigma} + e^{ikRi} C_{k,\sigma}^\dagger a_{i,\sigma}\} \\
 & + \sum_{q,k,\sigma} V_2(q) \{C_{k+q,\sigma}^\dagger C_{k,\sigma} b_q + b_q^\dagger C_{k,\sigma}^\dagger C_{k+q,\sigma}\}, \quad (1)
 \end{aligned}$$

where  $\varepsilon_k$  is the band energy with wave vector  $k$ .  $C_{k,\sigma}^\dagger$  and  $C_{k,\sigma}$  are the fermion creation and annihilation operators for electrons in oxygen  $2p$  bands.  $E_0$  is the orbitally nondegenerate  $3d^9$  energy level of Cu atom.  $a_{i,\sigma}^\dagger$  and  $a_{i,\sigma}$  are the Fermi creation and annihilation operators for electrons at site  $i$  in Cu  $3d^9$  orbital.  $b_q^\dagger$  and  $b_q$  are the phonon creation and annihilation operators.  $\hbar\omega_q$  is the energy of the phonons in the  $q$ th mode.  $V_1$  is the strength of hybridization between localized and band states.  $V_2(q)$  is the strength of the electron phonon interaction.

The energy levels  $\varepsilon_k$  and  $E_0$  are measured from the chemical potential and hence their values depend on the doping strength.

The Hamiltonian is brought from the site representation to the wave vector representation by defining the following relations

$$\begin{aligned}
 a_{i,\sigma}^\dagger &= 1/\sqrt{N} \sum_k a_{k,\sigma}^\dagger e^{-ikRi} \\
 a_{i,\sigma} &= 1/\sqrt{N} \sum_{k'} a_{k',\sigma} e^{ik'Ri}. \quad (2)
 \end{aligned}$$

After substituting and replacing the electron-phonon interaction terms with the Frohlich type electron-electron interaction term, the Hamiltonian becomes

$$\begin{aligned}
 H = & \sum_{k,\sigma} \varepsilon_k C_{k,\sigma}^\dagger C_{k,\sigma} + E_0 \sum_{k,\sigma} a_{k,\sigma}^\dagger a_{k,\sigma} \\
 & + U/2N \sum_{\substack{k_0, k_1, k_2 \\ \sigma, \sigma', \sigma - \sigma'}} a_{k_2+k_0,\sigma}^\dagger a_{k_1-k_0,\sigma'}^\dagger a_{k_1,\sigma} a_{k_2,\sigma} \\
 & + V_1 \sum_{k,\sigma} [a_{k,\sigma}^\dagger C_{k,\sigma} + C_{k,\sigma}^\dagger a_{k,\sigma}] \\
 & + \sum_{\substack{k,k' \\ q,\sigma,\sigma'}} V_2(k,k',q) C_{k+q,\sigma}^\dagger C_{k',\sigma'}^\dagger C_{k'+q,\sigma'} C_{k,\sigma} . \quad (3)
 \end{aligned}$$

Now consider the retarded Green's functions<sup>18</sup>

$$G_1 \equiv \langle\langle C_{k,\sigma}^\dagger(t); C_{k',\sigma'}(t') \rangle\rangle = \theta(t-t') \langle [C_{k,\sigma}^\dagger(t), C_{k',\sigma'}(t')] \rangle \quad (4)$$

$$G_2 \equiv \langle\langle a_{k,\sigma}^\dagger(t); C_{k',\sigma'}(t') \rangle\rangle = \theta(t-t') \langle [a_{k,\sigma}^\dagger(t), C_{k',\sigma'}(t')] \rangle . \quad (5)$$

The equation of motion for  $G_1$  and  $G_2$  will be

$$i \frac{d}{dt} G_1 = i\delta(t-t') \langle [C_{k,\sigma}^\dagger(t), C_{k',\sigma'}(t')] \rangle + \langle\langle [C_{k,\sigma}^\dagger(t), H]; C_{k',\sigma'}(t') \rangle\rangle \quad (6)$$

$$i \frac{d}{dt} G_2 = i\delta(t-t') \langle [a_{k,\sigma}^\dagger(t), C_{k',\sigma'}(t')] \rangle + \langle\langle [a_{k,\sigma}^\dagger(t), H]; C_{k',\sigma'}(t') \rangle\rangle . \quad (7)$$

When the commutators  $[C_{k,\sigma}^\dagger(t), H]$  and  $[a_{k,\sigma}^\dagger(t), H]$  are evaluated and substituted in Eqs. (6) and (7), we find that they contain terms with higher order Green's functions in addition to the terms with the lower order Green's functions  $G_1$  and  $G_2$ . These higher order Green's functions are decoupled by writing them as the product of correlation function and a lower order Green's function  $G_1$  or  $G_2$ . Thus Eqs. (6) and (7) become

$$i \frac{\partial}{\partial t} G_1 = i\delta(t-t') \delta_{\sigma,\sigma'} \delta_{k,k'} + P_2 G_1 - V_1 G_2 \quad (8)$$

$$i \frac{\partial}{\partial t} G_2 = P_1 G_2 - V_1 G_1 , \quad (9)$$

where

$$P_1 = - [E_0 + U/N + U/N \sum_{k_1} (a_{k_1,\sigma'}^\dagger a_{k_1,\sigma'})] \quad (10)$$

$$P_2 = - [\varepsilon_k + 2 \sum_{k',\sigma'} V_2(k' - k) \langle C_{k',\sigma'}^\dagger C_{k',\sigma'} \rangle] . \quad (11)$$

In obtaining the two equations of motion standard decoupling and approximation methods are adopted at the higher stage. The Fourier transform of the two equations of motion are found. Solving them,  $G_1(E)$  and  $G_2(E)$  are found.

$$G_1(E) = \frac{i/2\pi \delta_{kk'} \delta_{\sigma\sigma'}}{\{(E - P_2) - V_1^2/(E - P_1)\}} \quad (12)$$

and

$$G_2(E) = \frac{-i/2\pi \delta_{kk'} \delta_{\sigma\sigma'} V_1/(E - P_1)}{\{(E - P_2) - V_1^2/(E - P_1)\}} \quad (13)$$

Diagonalizing the set of coupled Fourier transform of the equations of motion, we get

$$G_{\pm} = U_k G_2(k, k', E) \mp V_k G_1(k, k', E) \quad (14)$$

with energies

$$E_{\pm} = [P_2 + P_1 \mp \sqrt{(P_1 - P_2)^2 + 4V_1^2}] \quad (15)$$

where  $U_k$  and  $V_k$  are given by

$$U_k = 1/\sqrt{2} \left[ 1 - \frac{(P_2 - P_1)}{\sqrt{(P_2 - P_1)^2 + 4V_1^2}} \right]^{1/2} \quad (16)$$

$$V_k = 1/\sqrt{2} \left[ 1 - \frac{(P_2 - P_1)}{\sqrt{(P_2 - P_1)^2 + 4V_1^2}} \right]^{1/2} \quad (17)$$

The system can be described as an assembly of noninteracting quasiparticles belonging to two different species, characterized by excitation energies  $E_{\pm}$  and the corresponding creation operators are

$$a_{\pm, \sigma}^{\dagger}(k) = U_k a_{k, \sigma}^{\dagger} \pm V_k C_{k, \sigma}^{\dagger} \quad (18)$$

Thus we are making a canonical transformation from the original set to a new set.

The various terms of the Hamiltonian are expressed in terms of the quasiparticle operators. By doing this, we intend to diagonalize the Hamiltonian. Expressing the original operators in terms of the new operators, we have substituted for various operators the combination of new operators. As expected, the Hamiltonian is not in the diagonal form. It contains off-diagonal terms of the form  $a_{+, \sigma}^{\dagger}(k) a_{-, \sigma}(k)$  and  $a_{-, \sigma}^{\dagger}(k) a_{+, \sigma}(k)$ . It also contains terms which involve four operators which do not satisfy the conservation of quasiparticle species. Such

terms are neglected. Those fourth order terms which conserve quasiparticle species are combined and their coefficient is equal to zero. Simplifying we get

$$V_2(k, k') = - U/2N [V_k^2 V_{k'}^2 / U_k U_{k'}] . \quad (19)$$

At 0 K very few quasiparticles are excited and hence the number operators for quasiparticles  $m_{+, \sigma}(k)$ ,  $m_{-, \sigma}(k)$  etc. have vanishingly small expectation values. Therefore off-diagonal terms and fourth order terms containing number operators are neglected.

Equating the coefficient of off-diagonal terms to zero, after simplification, we have

$$E_0 V_k^2 / U_k - \epsilon_k = - \sum_{k'} V_2(k, k') . \quad (20)$$

By using Eq. (19) for  $V_2(k, k')$ , Eq. (20) leads to

$$\frac{E_0 V_k^2}{U_k} - \epsilon_k = U/2N [V_k^2 / U_k] \sum_{k'} V_{k'}^2 / U_{k'} \quad (21)$$

putting  $U_k = (1/2 + x_k)^{1/2}$  and  $V_k = (1/2 - x_k)^{1/2}$ .

By substituting  $U_k$  and  $V_k$  and then putting

$$U/2N \sum_{k'} \left[ \frac{(1/2 - x_{k'})}{(1/2 + x_{k'})} \right] = \Delta_k(0) \quad (22)$$

we obtain

$$x_{k'} = \frac{1/2(E_0 - \Delta_{k'}) - \epsilon_{k'}/2}{(E_0 + \epsilon_{k'} - \Delta_{k'})} . \quad (23)$$

Substituting for  $x_{k'}$  in the equation for  $\Delta_k$ , the energy gap at 0 K leads to

$$\Delta_k(0) = U/2N \sum_{k'} \frac{\epsilon_{k'}}{\{E_0 - \Delta_k(0)\}} . \quad (24)$$

Assuming  $\Delta_k$  as slowly varying with  $k$  and introducing  $D(\epsilon_k)$  as the density of localized states per Cu atom, we get

$$\Delta_k(0) = \frac{U}{2\{E_0 - \Delta_k(0)\}} \int_0^{\epsilon_{k_0}} D(\epsilon_{k'}) \epsilon_{k'} d\epsilon_{k'} , \quad (25)$$

where  $\epsilon_{k_0}$  is the upper bound of the hybridized  $2p$  bands, and  $D(\epsilon_k)$  is the density of localized states per Cu atom. For each value of  $\epsilon_k$  there are two values of

$\omega$  and hence we have to sum the two density of states corresponding to  $E_+$  and  $E_-$ . Linear relations are assumed to hold between the doping strength  $x$  and the parameters  $E_0$ ,  $\varepsilon_{k_0}$  and  $V_1$ .

Since the Fermi level decreases linearly with doping, the relationship between  $E_0$  and the doping strength  $x$  will be  $E_0 = R_1 x + 0.5$ . In the undoped case  $x = 0$ , the localized Cu state and the narrow  $2p$  band of oxygen atoms are of nearly equal energy. This justifies the introduction of the small energy difference 0.5 between the upper bound of the  $2p$  band and the Cu  $3d^9$  level.  $\varepsilon_{k_0}$  is the top most level of the  $2p$  band as measured from the Fermi level and hence the relation  $\varepsilon_{k_0} = R_2 x$  holds. The hybridization parameter  $V_1$  should change with the overlapping integral which in turn has a linear dependence on the concentration of the dopants in the out of the plane sites. Therefore we choose  $V_1 = V_{10} + R_3 x$ , where  $V_{10}$  stands for the residual mixing parameter.

We have assigned the following numerical values.  $R_1$ ,  $R_2$ , and  $R_3$  are given the values 2.0, 2.0, and 0.2, respectively.  $V_{10} = 0.05$ ,  $V_2 = -0.056$  eV,  $U = 6.0$  eV and the density of band states per Cu atom = 1.0.

The set of equations for the Green's functions are solved and the correlation functions in  $P_1$  and  $P_2$  are found by iterative computation. For  $x = 0.19$ , the computed values are

$$2 \sum_k V_2 \langle C_{k,\sigma}^\dagger C_{k,\sigma} \rangle = -0.8866886 \times 10^{-5} \quad \text{and}$$

$$1/N \sum_k \langle a_{k',\sigma'}^\dagger a_{k,\sigma'} \rangle = 0.7841363 \times 10^{-4} .$$

The density of localized states is calculated using Green's function technique with the help of a digital computer. Substituting for the density of states, the integration is performed and hence  $\Delta_k(0)$  is calculated. Corresponding to  $x = 0.19$ ,  $\Delta_k(0)$  has the value  $6.4326 \times 10^{-3}$  eV and  $2\Delta(0)/k_B T_c = 3.739$  for a  $T_c = 40$  K.

Detailed calculation of the variation of energy gap with doping strength and temperature will be published elsewhere. The mixing parameter is determined by the overlap integral of the band states with the localized states of Cu atom. This integral is determined by the ordering of the out of the plane dopants, which have a quasi periodic character.

#### Acknowledgments

S. V. V. would like to thank the C. S. I. R., New Delhi for the award of Junior Research Fellowship and V. M. N. wishes to acknowledge the U. G. C., New Delhi for financial assistance.

#### References

1. J. G. Bednorz and K. A. Müller, *Z. Phys.* **B64** (1986) 188.

2. P. H. Hor, L. Gao, R. L. Meng, Z. J. Huang, Y. Q. Wang, K. Forster, J. Vassilions, C. W. Chu, M. K. Wu, J. R. Ashburn, and C. J. Torng, *Phys. Rev. Lett.* **58** (1987) 911.
3. J. Bardeen, N. Cooper, and J. R. Schrieffer, *Phys. Rev.* **108** (1957) 1175.
4. C. R. Leavens, *Solid State Commun.* **17** (1975) 1499.
5. W. L. McMillan, *Phys. Rev.* **167** (1968) 331.
6. B. R. Batlogg, R. J. Cava, A. Jayaraman, R. B. Van Dover, G. A. Kouronklin, S. Sunshine, D. W. Murphy, L. W. Rupp, H. S. Chen, A. White, K. T. Short, A. M. Mjuscce, and E. A. Rietman, *Phys. Rev. Lett.* **58** (1987) 2333.
7. J. D. Jorgensen, H. B. Schuttler, D. G. Hinko, D. W. Copone, K. Zang, M. B. Brodsky, and D. J. Scalapino, *Phys. Lett.* **58** (1987) 1024.
8. J. Yu, A. J. Freeman, and J. H. Xu, *Phys. Rev. Lett.* **58** (1987) 1035.
9. Y. Hidaka, Y. Enomoto, M. Suzuki, M. Oda, and T. Murakami, *Jpn. J. Appl. Phys.* **26** (1987) L377.
10. T. R. Dinger, T. K. Worthington, W. J. Gallagher, and R. L. Sandstrom, *Phys. Rev. Lett.* **58** (1987) 2687.
11. M. Nucker, J. Fink, J. C. Fuggle, P. J. Durham, and W. M. Temmerman, *Phys. Rev.* **B37** (1988) 5158.
12. P. Steiner, S. Hufner, V. Kinsinger, I. Sander, B. Siegart, H. Schmitt, R. Schulz, S. Junk, G. Schwitzgebel, A. Gold, C. Politis, H. P. Muller, R. Hoppe, S. Kemmler Sack, and C. Kunz, *Z. Phys.* **B69** (1988) 449.
13. M. W. Shafer, T. Penney, and B. L. Olson, *Phys. Rev.* **B36** (1987) 4047.
14. P. W. Anderson, *Science* **235** (1987) 1196.
15. J. Hubbard, *Phys. Rev.* **B17** (1978) 494.
16. P. W. Anderson, *Phys. Rev.* **124** (1961) 41.
17. H. Fröhlich, *Proc. Roy. Soc. London* **A215** (1952) 291.
18. S. V. Tyablikov, in *Methods in the Quantum theory of Magnetism* (Plenum, 1967).